



B8103

weefsel/tissu/fabric Gewebe/tejido		100% PES 1100 dtex	
gewicht/poids/weight Gewicht/peso total		650 g/m ²	DIN EN ISO 2286-2 BS 3424 method 5A
samenstelling composition composition Zusammensetzung composición	doek/tissu/fabric Gewebe/tejido coating/enduction Beschichtung/revestimiento	180 g/m ² 470 g/m ²	DIN EN ISO 2286-2 BS 3424 method 5B
vernis/lacquering/Lackierung/lacado		2/2	
treksterkte résistance rupture breaking strength Höchstzugkraft resistencia a la ruptura	ketting/warp/chaîne Kette/urdimbre inslag/weft/trame Schuß/trama	2500 N/5cm 2300 N/5cm	DIN 53 354 BS 3424 method 6A
scheurweerstand résistance à la déchirure tear strength Weiterreißfestigkeit resistencia a la rasgadura	ketting/warp/chaîne Kette/urdimbre inslag/weft/trame Schuß/trama	270 N 270 N	DIN 53 363
hechting/adhérence/adhesión Haftung/adherencia		90 N/5cm	DIN 53 357 BS 3424 method 9B
temperatuurbestendigheid tenue à la température temperature resistance Temperaturbeständigkeit resistencia a la temperatura		-30 °C/+70°C	DIN EN 1876-2 BS 3424 method 10
lichtechtheid tenue à la lumière light fastness Lichtechtheit resistencia a la luz	(uitgezonderd wit) (excepté en blanc) (except white) (außer Weiß) (excepto blanco)	7-8	DIN EN ISO 877 BS 3424 method 15
onbrandbaarheid/inflammabilité flammability/Flammbarkeit/inflamabilidad		M2	NF P 92-507 DIN 4102-B1 NFPA 701 Smallscale California Fire Marshal Title 19
toepassing application application Anwendung aplicación	tenten en scooters, alu-structuren (M2) tentes et chapiteaux forains, toile pour structures (M2) tents and scooters, aluminium structures (M2) Zelte, Scooters, Textiles Bauen (M2) carpas para estructuras (M2)		